

A Thermochemical Framework for Ruby-Sapphire Heat Treatment: Intrinsic and Extrinsic Regimes, Treatment Parameters

Author: Ted Themelis

Affiliation: Independent Researcher, Gemlab, Bangkok, Thailand

ORCID: 0000-0002-4493-6623 **Email:** ted@themelis.com

Version: 1 **Date:** October 2026

Document Type: Framework Overview / Extended Summary of the book

First Principles of the Thermochemistry of Ruby & Sapphire (2026; ISBN 0-940965-51-8; forthcoming)

Keywords: corundum, ruby, sapphire, heat treatment, thermochemistry, oxygen partial pressure, thermodynamic framework, intrinsic and extrinsic regimes, defect chemistry

Abstract

This paper introduces a systematic materials science framework designed to evaluate the chemistry of imperfect ruby-sapphire crystals during thermal processing. Historically approached as an empirical craft, the heat treatment of corundum is reframed here through the principles of thermodynamics and defect chemistry. We delineate the operational boundaries between intrinsic and extrinsic reaction regimes, identify the critical triaxial heating parameters, and establish the specialized hardware requirements necessary to execute advanced thermochemical alterations under a fully controlled environment. The framework draws on more than 3,000 selected heating experiments over four decades and summarizes the companion book *First Principles of the Thermochemistry of Ruby & Sapphire* (2026; ISBN 0-940965-51-8; forthcoming).

Introduction

This framework is developed from more than four decades of experimental work in the thermal processing of ruby and sapphire. Over this period, more than 3,000 selected heating experiments were executed, with detailed operational notes and empirical observations meticulously retained and classified. This work, about 650 pages in total, is presented in the *Fourth Edition of The Heat Treatment of Ruby & Sapphire* (currently under preparation) and in a companion standalone book, *First Principles of the Thermochemistry of Ruby & Sapphire* (2026), which develops in full the thermochemical framework summarized here. Since 2002, a practical training curriculum focusing on the thermochemistry of corundum has been conducted in Bangkok by the author, providing technical instruction to hundreds of members of the gem and jewelry industry over the past twenty-four years. This paper unifies those field-level observations within a solid-state thermodynamics framework.

1. The Subject of Thermochemistry

In simplest terms, the thermochemistry of ruby-sapphire may be defined as the materials science concerned with the chemistry of imperfect ruby-sapphire crystals as a whole and of their component parts. At one and the same time, it is both more restricted and more extensive in scope than gemology. The thermochemistry of ruby-sapphire deals with the distribution and migration of chemical elements within the corundum lattice, and how to manage them. It may be considered as an introduction to thinking about ruby-sapphire heat treatment thermochemically.

Every ruby-sapphire may be regarded as a chemical system in which, through heat and related parameters, chemical changes occur under different environments. Each change disrupts the existing equilibrium of the crystal, driving the transformation toward a new system that remains stable under these altered conditions.

The study of these changes is the subject of thermochemistry in ruby-sapphire. To determine what changes are possible, how and where they occur, to observe the phenomena that accompany them, and to note their final outcomes are among the core functions of thermochemistry.

From a thermochemical perspective, the ruby-sapphire crystal is the main object of study. The reactions that take place within it may be classified under two regimes: first, reactions due to intrinsic elements; second, reactions due to externally introduced chemical compositions. Much valuable information is derived from laboratory experiments and is essential for the verification of these outcomes.

No account of the thermochemistry of ruby-sapphire as a unified subject has yet been published in the literature. The closest prior work, Emmett et al. (2003), addresses beryllium diffusion specifically and does not attempt a unified treatment. Thermochemical data remain scattered across separate studies of color, inclusions, diffusion, and furnace practice. This framework gathers these data points into a single, unified treatment, building on the defect chemistry of Kröger and Vink (1956) and Kröger (1974), the transition-metal spectroscopy of Eigenmann and Günthard (1972), and the historical record of Nassau (1994).

2. The Benefits of a Thermochemical Framework

Ruby-sapphire heat treatment is often approached empirically: a stone is heated under specific heating parameters, and the result is judged solely by the observed outcome. While this approach can produce useful results, it does not necessarily explain why a result occurred, or why the same treatment may behave differently in another stone.

A thermochemical approach offers a different way of observing the heating process. Instead of treating temperature as the primary variable, it considers the combined effects of temperature, chemical potential, atmosphere, defects, phase stability, redox reactions, and diffusion. The benefits of this approach extend directly to several key groups:

The treater-experimentalist evaluates the outcome of a heated stone by comparing it against the specific technique or recipe applied. Within a thermochemical framework, color modification, inclusion dissolution, and defect alterations become interconnected processes rather than isolated events. Unsatisfactory results indicate unsuitable parameters applied for the particular type of ruby-sapphire under these conditions in the heating process. Reheating the stone under a different technique, recipe, or set of parameters remains a common option to optimize the outcome, though it is routinely executed without knowing the causative reasons behind the chemical transformations.

The gemologist and the laboratory analyze a heated stone to document the empirical indicators of treatment, relying on different levels of analytical instrumentation with inherent limitations. Mapping these descriptive visual and spectral features to generalized processing environments helps clarify the broad history of a stone, explaining why two crystals from the same origin can exhibit vastly different appearances after heating.

The scientific community gains a documented body of experimental observations, gathered over four decades and framed in the language of thermodynamics and defect chemistry. These observations can be tested, extended, verified, or challenged in the laboratory, provided that the experimental samples match the specific criteria and crystal characteristics described in this work.

This framework does not eliminate the empirical nature of heat treatment, since experimental observation remains essential. Instead, the purpose of this framework is to examine what changed, what caused the change, and what conditions must exist for the process to occur. The result is not a collection of treatment recipes. It is a framework for understanding the chemistry of ruby-sapphire during heating, making experimental observations more meaningful and more transferable from one heating system to another.

3. The Regimes: Intrinsic vs. Extrinsic

Every thermochemical reaction examined in this work is classified according to one criterion: whether the chemical change originates entirely within the native composition of the crystal, or whether it depends on a chemical composition externally introduced to the ruby-sapphire crystal during heating.

For classification purposes, a reaction is assigned to a regime according to the origin of the chemical composition responsible for the reaction. In practice, however, the two regimes can interact dynamically once an additive is introduced.

This distinction serves as the organizing principle behind the structural framework of the science. The intrinsic regime is evaluated in full isolation before addressing the extrinsic regime. This approach prevents externally introduced chemical compositions from becoming entangled with the native defect chemistry that governs every stone in the system, regardless of its origin.

Intrinsic Regime (Non-Additives): The intrinsic regime comprises thermochemical reactions that draw exclusively on chemical elements and structural defects already present in the ruby-sapphire crystal prior to heating—its native trace-element load, existing point and line defects, and the oxygen and cation sublattices of the corundum structure itself. Redox reactions that shift the ionic balance, the dissolution of pre-existing rutile silk, and defect formation or annihilation driven by atmosphere and temperature all belong to this regime. The furnace controls the temperature profile and atmospheric conditions, but introduces no added composition intended to become part of the finished stone.

Extrinsic Regime (Additives): The extrinsic regime comprises reactions that depend on a chemical composition introduced externally to the crystal during heating. These compositions can be grouped into distinct classes by composition and role based on their specific chemical mechanisms. For most additive-treated rubies reaching the trade, the primary purpose of these extrinsic additives is clarity improvement: filling void-type defects—such as surface-reaching fractures, cavities, and porosity—that limit transparency. Chromophoric additives, used to alter color, belong to the same extrinsic regime but act mainly by lattice diffusion rather than void filling.

The intrinsic and extrinsic regimes are not chemically isolated from one another once an additive is present. As the introduced composition interacts with the host, the intrinsic elements of the ruby-sapphire are drawn into the reaction—forming new compositions with the additive or altering compositions already present in the crystal. In some cases, the interaction extends beyond chemistry: additive-driven reactions have been observed to alter the physical properties of the host itself, rather than altering merely the optical or compositional state.

4. The Core Alteration Mechanisms

Whatever the process, four types of thermochemical or thermomechanical changes may be involved in the heated ruby-sapphire as follows:

- 1. Redox Engineering:** Adjusting the furnace atmosphere so the trace elements responsible for color can change their oxidation states.
- 2. Phase and Inclusion Control:** Managing internal inclusions as they dissolve, form, or change shape as allowed by heat and time.
- 3. Defect Engineering:** Deliberately creating, healing, or redistributing the internal structural imperfections of the crystal.
- 4. Thermomechanical Control:** Managing heat and stress to ensure the stone survives the process intact.

Gemology describes what is observed; thermochemistry explains why it occurs and how it can be controlled. In practice, each of these four processes is steered through the three furnace-side parameters described in

Section 5: atmospheric environment, temperature, and additives. Within this framework, gemology and thermochemistry function as complementary, rather than competing, disciplines.

5. The Triaxial Heating Parameters

In processing any classification of ruby-sapphire, the core execution strategy relies on three interdependent variables that define the thermochemical environment within the furnace chamber. Every heating protocol occupies a specific coordinate along these three axes (Figure 1):

- **Atmosphere Composition:** Regulating oxygen partial pressure (pO_2) across a wide operational spectrum, ranging from highly reducing environments (pO_2 of the order of 10^{-15} bar and below) to highly oxidizing, oxygen-rich environments.
- **Thermal Profile:** Managing the temperature range (typically 1000°C to 1800°C , occasionally as low as 800°C) alongside precise rates of heat-up, isothermal soaking, and cool-down.
- **Chemical Additives:** Introducing specific chemical compounds, fluxes, or reagents that interact directly with the corundum host.

These three parameters operate at a total furnace pressure of 1 atm (approximately 1 bar); pressure is therefore not treated as an independent variable in this framework. They apply universally to both natural and synthetic crystals, independent of the underlying equipment design or specific furnace configurations.




Figure 1. Conceptual triaxial diagram of the key heating parameters of ruby-sapphire: temperature (heating profile), atmosphere, and chemical additives. Every heating protocol occupies a position along these three axes, applied at 1 atm (approximately 1 bar) total pressure (original diagram © T. Themelis, 1999).

Reading Figure 1. The diagram is a map of every heating process applied to ruby-sapphire at 1 atm. The vertical axis is the atmosphere, running from reducing (low oxygen, pO_2 of the order of 10^{-15} bar) at the top to oxidizing (oxygen-rich, up to 99.999% O_2) at the bottom. The horizontal axis is temperature and heating profile, running from about 800°C (minimum) to 1800°C or slightly above (practical maximum). The circular band represents chemical additives, which may be introduced at any point of the map. Any heating protocol, of any type, on any ruby-sapphire, is therefore located by three coordinates: where it sits on the atmosphere axis, where it sits on the temperature and heating-profile axis, and whether (and which) chemical additives are present. Every thermochemical event discussed in this framework takes place somewhere within this diagram. For example, the blue treatment of a dark geuda typically sits on the reducing, high-temperature side of the map, whereas the treatment of a pink sapphire sits on the oxidizing side at lower temperature.

6. Technology and Equipment Requirements

The evaluation of these processes depends heavily on the capabilities of the operator and the instrumentation:

- **Heat-Treating Technology (“Know-How”):** Defines the specific thermodynamic and environmental parameters required to induce a targeted transformation within a given classification of corundum. This framework integrates the three primary process-control parameters established above—atmosphere, temperature, and additives, applied at 1 atm—to formulate a systematic treatment strategy.
- **Heating Equipment Technology (“Furnace”):** Encompasses the specific hardware configurations and engineering systems utilized to physically execute the thermodynamic parameters defined by the heat-treating technology (“know-how”). This engineering category includes electric resistance, combustion, and specialized furnace systems configured to operate under diverse environments with dedicated process controls.

In practice, these two technologies are rarely integrated into a single commercial package within the gemstone sector. A general-purpose furnace system lacks the specialized capability required to execute advanced thermochemical applications under a fully controlled environment. Furnace architectures are treated in detail in the monograph series. A suitable furnace system must provide the operational flexibility required to execute all heating parameters within the technical boundaries and limitations defined by materials science. Closing that gap, one technology and one process at a time, is the core purpose of the forthcoming monograph editions.

Bibliography: Foundational Literature

The references below carry the reader from established defect theory, through the historical record of empirical heat-treating, to the point where this framework—and the monographs that follow it—begin.

Eigenmann, K., & Günthard, H. H. (1972). “Valence states, spectra and exchange interactions of Cr, Mn, Fe, and Ni in α -Al₂O₃.” *Helvetica Physica Acta*, 45, 1141–1170.

Component Role: Focuses on the exact chemistry of the transition metals that give ruby and sapphire their colors, tracking how their valences change under thermal treatment.

Emmett, J. L., Scarratt, K., Shane, S. F., et al. (2003). “Beryllium Diffusion of Ruby and Sapphire.” *Gems & Gemology*, 39(2), 84–135.

Component Role: Discusses the thermodynamics of trace element diffusion, oxidation states, and lattice reactions.

Kröger, F. A., & Vink, H. J. (1956). “Relations between the Concentrations of Imperfections in Crystalline Solids.” *Solid State Physics*, 3, 307–435.

Component Role: Establishes the theoretical solid-state physics of point defects that this framework applies directly to active gemstone modification.

Kröger, F. A. (1974). *The Chemistry of Imperfect Crystals* (2nd ed.). North-Holland Publishing.

Component Role: Provides the thermochemical behavior of point defects in metal oxides, which applies directly to corundum.

Nassau, K. (1994). *Gemstone Enhancement: History, Science and State of the Art* (2nd ed.). Butterworth-Heinemann. ISBN 0-7506-1797-7.

Component Role: Provides the historical, empirical starting point for ruby-sapphire heat treatment on which this framework builds.

Themelis, T. (1992–2026). *The Heat Treatment of Ruby & Sapphire*. 1st ed., USA, published by the author, 1992, ISBN 0-940965-10-0; 2nd ed., Thailand, published by the author, 2010, ISBN 0-940965-11-9; 3rd

ed., Thailand, published by the author, 2018, ISBN 0-940965-57-7; 4th ed., Thailand, published by the author, 2026 (forthcoming), ISBN 0-940965-60-7.

Component Role: Documented the baseline empirical recipes, furnace histories, and macro-level gemstone reactions from an operative, field-level perspective.

Themelis, T. (2024). *First Principles in Heating Ruby-Sapphire* (Monograph No. 2, 2024 edition; out of print). Thailand, published by the author. ISBN 0-940965-27-5.

Component Role: The 2024 edition of Monograph No. 2 in the twelve-monograph series. Its thermochemical content is expanded into the standalone 2026 book below; a new, shorter treater-level edition of Monograph No. 2 is in preparation as *Fundamentals of Heating Ruby-Sapphire*, part of *The Heat Treatment of Ruby & Sapphire*, 4th ed. (ISBN 0-940965-60-7).

Themelis, T. (2026). *First Principles of the Thermochemistry of Ruby & Sapphire*. Thailand, published by the author. ISBN 0-940965-51-8. Forthcoming.

Component Role: The full thermochemical treatment of which this paper is the framework summary, including the intrinsic and extrinsic regimes and the triaxial heating parameters.

Supporting Bibliography

Supporting references on selected isolated topics and passages related to thermochemistry, in the form of published articles and papers, are given at the end of the full book.