BLUE SAPHIRE BLUEPRINT: The Etiology of Mechanical and Atmospheric Failure: A Thermodynamic and Engineering Analysis in Gas-Oxy Combustion Furnaces

AUTHOR: Ted Themelis
AFFILIATION: Independent Researcher
ORCID: 0000 0024493 6623
Email: *ted@themelis.com*
© 2026 T. Themelis. *All rights reserved. No part of this work may be reproduced, translated, or redistributed without the prior written permission of the author.*

Abstract
The heat treatment of geuda sapphire to produce stable blue coloration remains highly variable in gas-fired furnace systems, despite decades of empirical practice. This study examines the thermodynamic and engineering factors underlying this variability by linking lattice-scale color mechanisms to the macroscopic behavior of fuel-rich LPG–oxygen combustion atmospheres in Lakmini furnaces.

Blue coloration in sapphire arises from the electronic transition associated with iron–titanium (Fe^{2+}–Ti^{4+}) intervalence charge transfer (IVCT), which is stabilized only within a narrow oxygen-potential pO_2) window at elevated temperatures. This operational window is bounded by two practical combustion landmarks: the Titration Point (TP), marking the transition to the optimal partial-oxidation regime for reducing-gas production, and the Soot Disappearance Boundary (SDB), which defines the upper limit of clean, soot-free combustion under fuel-rich conditions. Deviations beyond either boundary destabilize these color-producing defect states through oxidation, over-reduction, or surface masking.

Using a synthesis of crystallographic considerations, combustion analysis, and four decades of industrial field observations, this work demonstrates that treatment failure most commonly arises not from incorrect target conditions, but from cumulative mechanical and atmospheric deviations. Variability in LPG composition, air-calibrated flow instrumentation, burner fouling, refractory degradation, and atmospheric stratification collectively shift the effective pO_2 away from the stable blue regime—often without detectable changes in nominal operating settings. This results in a diagnostic framework that moves sapphire heat treatment toward a thermodynamically grounded, systems-level understanding of failure etiology.

KEYWORDS: *Geuda corundum; LPG–oxygen stoichiometry; Titration Point; Soot Disappearance Boundary; oxygen partial pressure (pO_2); Redox stability; Fe^{2+}–Ti^{4+} intervalence charge transfer; Solid-state diffusion; Lakmini furnace; failure analysis.*

Introduction

The heat treatment of geuda-type sapphires is a cornerstone of the Sri Lankan gemstone industry. By subjecting these stones to extreme temperatures, typically in Lakmini gas-oxygen furnaces, practitioners transform pale, translucent corundum into high-value blue sapphire. These systems utilize liquefied petroleum gas (LPG) and oxygen to generate the specific thermal and chemical environments—specifically, a tightly controlled reducing atmosphere—essential for color development.

Successful blue coloration depends on stabilizing the Fe^{2+}–Ti^{4+} interaction within the crystal lattice. This process is governed by the oxygen partial pressure (pO_2) maintained throughout the high-temperature soak; the atmosphere must be neither excessively oxidizing nor overly reducing. In traditional gas-fired systems, this environment is managed indirectly via the LPG-to-oxygen ratio. Because direct atmospheric sensing at extreme temperatures is often technically or economically impractical, the operator is forced to rely on a proxy that is highly sensitive to external variables such as burner geometry and fuel-composition drift.

Historically, successful treatment was attributed to the intuition and "secret recipes" of the furnace operator. However, even when nominally identical procedures are followed, outcomes remain

inconsistent, leading to significant economic loss for an industry valued at approximately $360 million (official). Modern production standards require a more rigorous transition from empirical "recipes"—which often mistake correlation for causation—to a systems-level understanding of the process. This paper establishes a diagnostic framework that integrates sapphire mineralogy, oxygen thermodynamics, and furnace engineering to analyze treatment failures across three interdependent sectors:

- **Part A:** Intrinsic variations in geuda precursor chemistry;
- **Part B:** Thermodynamic and kinetic constraints on color formation; and
- **Part C:** Mechanical and flow-dynamic inconsistencies within gas-fired systems.

By reconciling high-temperature diffusion processes with combustion engineering, this study aims to clarify the underlying mechanisms of recurrent treatment failure. Recognizing that physics possesses no secrets—only fundamental constants—the resulting framework provides a consistent basis for interpreting color outcomes, diagnosing atmospheric drift, and aligning empirical observations with established thermodynamic principles.

PART A. INTRINSIC VARIATIONS IN GEUDA COMPOSITION

2. Chemical Composition and Color Potential

The capacity for a geuda sapphire to transform into a vibrant blue specimen depends fundamentally on the trace element profile inherent to the stone. The most critical elements are iron (Fe) and titanium (Ti). Although these elements are present in minute concentrations—measured in parts per million (ppm)—they exert primary control over the gemstone's color behavior during the heat treatment process.
Typical geuda and sapphire samples contain iron concentrations ranging from several hundred to several thousand ppm, while titanium levels are generally lower, occurring between a few tens and a few hundred ppm. Stones possessing both elements within these compatible ranges harbor the latent potential for blue color development.

However, the mere presence of iron and titanium does not ensure a successful outcome. The specific ratio between these two elements, along with the influence of secondary trace elements, significantly dictates the final result. Magnesium (Mg), in particular, can inhibit the color-forming mechanism by competing with iron for interactions with titanium. In such instances, the stone may exhibit a weak color response or remain entirely colorless, even when subjected to ideal furnace conditions.

Other trace elements further refine the final aesthetic of the sapphire. For example, trace amounts of chromium (Cr) may introduce a purplish tint, while vanadium (V) can modify the hue under specific oxidation-reduction (redox) conditions. While these effects are generally secondary, they become prominent in stones with borderline chemical compositions.

In summary, the chemical composition of the corundum establishes the maximum potential for color enhancement. While precise furnace control is required to realize this potential, it cannot supersede the fundamental chemical constraints established within the stone's crystal lattice.

PART B. THERMODYNAMIC & KINETIC CONTSTRAINS ON COLOR FORMATION

3. Color Mechanism

Blue coloration in sapphire arises from interactions between iron and titanium within the corundum lattice, producing defect-related electronic states that absorb light in the yellow–red region of the visible speFig. 1ctrum. The resulting selective absorption yields the characteristic blue transmission.

Early, classical models describe this mechanism as intervalence charge transfer (IVCT) between Fe^{2+} and Ti^{4}, involving electron transfer between adjacent ions *(Burns & Strens, 1966; Burns, 1970).* While this model remains a useful conceptual framework, recent spectroscopic studies indicate that most iron in

heat-treated sapphire persists in the Fe^{3+} state even after high-temperature exposure *(Thammajaka & Klondona, 2023).*

This observation suggests that blue color development does not require bulk reduction of iron throughout the crystal. Instead, coloration is attributed to localized iron–titanium defect environments that function as discrete color centers within an otherwise largely unchanged lattice. On this basis, the present study adopts a charge-balance pair description, treating iron–titanium defects as locally stabilized electronic configurations rather than uniformly reduced ionic species. This interpretation is consistent with both classical color theory and contemporary spectroscopic evidence.

The formation and stability of these defect states are governed by coupled thermodynamic and kinetic constraints during heat treatment. Furnace oxygen potential controls the stabilization or neutralization of iron–titanium pairs, while soak temperature and duration regulate atomic diffusion and defect rearrangement. Heating and cooling rates further influence strain development and defect retention. Stable blue coloration is achieved only when these parameters remain within narrow ranges that support the formation and preservation of color-producing defect states.

At treatment temperatures, the establishment of iron–titanium defect states is necessarily coupled to the partial dissolution of rutile inclusions and the subsequent mobility of titanium within the corundum lattice, both of which are regulated by the prevailing oxygen potential.

The stability and quality of these defect states are governed by several critical processing variables:

- **Heating Rate:** Excessively rapid heating can induce mechanical strain and structural defects that scatter light, ultimately weakening the perceived color.
- **Oxygen Potential:** The availability of oxygen determines whether the iron-titanium defect states are stabilized or neutralized.
- **Soak Temperature:** Sustained high temperatures facilitate the rearrangement of defects and vacancies into color-producing configurations.
- **Soak Time:** Adequate duration is required for the necessary atomic diffusion and defect equilibration to occur.
- **Cooling Rate:** The speed of cooling dictates whether these color-producing states are preserved or lost as the furnace returns to ambient temperature.



Fig. 1. The absorption spectrum of blue sapphire (Nassau, 2001).

Successful blue coloration is achieved only when each of these factors is maintained within the specific thresholds required for stability.

4. Operational Atmospheric Regimes

During sapphire heat treatment, the furnace atmosphere does not exist as a single, fixed chemical state. Instead, it passes through a series of operational regimes governed by the combustion dynamics of LPG and oxygen at elevated temperatures. These regimes are practical descriptors of furnace behavior rather than representations of exact equilibrium gas compositions.



Fig. 2. Schematic thermodynamic trajectory of effective oxygen chemical potential during blue sapphire heat treatment at ~1650 °C, expressed as log (pO_2/atm), as a function of the imposed LPG:O_2 fuel-to-oxidizer ratio. The vertical axis represents decreasing oxygen potential, from oxidizing conditions (≈10^0–10-7 atm) to strongly reducing conditions (≈10^{-13}–10^{-14} atm and beyond). The horizontal axis denotes the imposed, uncompensated volumetric LPG:O_2 ratio as controlled operationally.
The quasi-linear curve represents a practical reference trajectory in oxygen-potential space, reflecting the extreme sensitivity of oxygen chemical potential to marginal stoichiometric perturbations under high-temperature, fuel-rich combustion. Two empirically defined combustion landmarks bound critical segments of the trajectory: the titration point (TP) at $pO_2 \approx 10^{-9}$ atm, marking the onset of strong CO/CO_2 buffering, and the soot disappearance boundary (SDB) at $pO_2 \approx 10^{-11}$ atm, below which carbon stability and soot formation become thermodynamically favored.
Three principal operational regimes are distinguished along the trajectory:
(i) Oxidizing regime, above the TP, where high oxygen activity destabilizes blue color centers and favors Fe^{3+}-dominated states;
(ii) Optimal blue coloration (bluing) window, between the TP and SDB, where sub-stoichiometric conditions stabilize Fe^{2+}–Ti^{4+} intervalence charge transfer (IVCT) and charge-compensated defect states within the corundum lattice;
(iii) Strongly reducing, carbon-controlled regime, below the SDB, where excess fuel promotes hydrocarbon cracking, carbon deposition, and progressive reduction of iron oxides toward metallic iron, producing gray to black coloration and metallic surface markings.
This schematic is illustrative and operational in nature and is not intended to represent a calibrated equilibrium or kinetic model. (Themelis, 1988-2025).

Oxidation regime. At the oxidizing extreme, oxygen is abundant. While such conditions are suitable for the treatment of certain yellow, orange, or pink corundum varieties, they are incompatible with blue sapphire formation. Under oxidizing atmospheres, iron–titanium defect states are destabilized, resulting in weak coloration or complete color loss.

Between oxidizing and strongly reducing conditions lies a transitional regime characterized by atmospheric instability with respect to blue color formation. In this region, small fluctuations in gas flow, temperature, or mixing efficiency can shift the furnace toward either oxidation or excessive reduction, leading to inconsistent and unpredictable outcomes.

CO_2/H_2 Buffered Regime. Stable blue coloration develops only within a narrow, moderately reducing regime. In this window, oxygen partial pressure is sufficiently low to stabilize iron–titanium defect states, yet not so low as to promote metallic effects or carbon deposition. This interval defines the critical operational zone in which blue color can form and be retained during the soak.

Soot-Stable Carbon Buffered Regime. As oxygen availability decreases further, the furnace approaches the Titration Point (TP), where combustion efficiency reaches its practical maximum under fuel-rich conditions. Immediately beyond this lies the Soot Disappearance Boundary (SDB), marking the final

clean-burning threshold before the onset of visible soot. Operation below the SDB corresponds to a strongly reducing, carbon-rich regime.

Under extreme reducing conditions, soot formation, carbon deposition, and metallic masking become increasingly likely. In such environments, stones may appear gray, opaque, or metallic, effectively obscuring blue coloration even when iron and titanium concentrations are otherwise favorable.

These atmospheric regimes should be understood as operational categories rather than fixed chemical constants. Local variations in gas flow, burner geometry, turbulence, and furnace loading can produce spatial overlap of regimes within a single furnace. Consequently, maintaining a stable environment within the blue-color window requires consistent control of combustion parameters and reliable furnace hardware performance.

5. Thermal Processing Parameters

5.1. Operating temperature. Successful blue sapphire heat treatment requires not only appropriate atmospheric control but also rigorous management of thermal conditions. Although flame temperatures in Lakmini gas–oxygen furnaces may locally approach 1900–1950 °C, the effective temperatures used for blue color development are lower and must be more precisely regulated.

In practice, color enhancement is typically achieved at soak temperatures in the range of approximately 1650–1700 °C. This thermal interval is sufficient to promote dissolution of rutile (TiO_2) inclusions and to activate the diffusion of titanium and associated lattice defects. Temperatures below this range lead to sluggish diffusion and incomplete color development, whereas excessive temperatures increase the risk of lattice damage, surface corrosion, and uncontrolled chemical reactions.

Fig.3. Results from a mixed geuda sapphire lot following a 3-hour thermal cycle in a gas-fired Lakmini furnace at approximately 1650 °C. Flowmeter settings were maintained at 4.5 (LPG) and 24.5 (O_2), corresponding to an indicated LPG:O_2 ratio of ~1:5.44. Despite uniform furnace operating conditions, the treated stones exhibit a wide chromatic distribution, ranging from pale blue and saturated blue to dark blue-gray and near-black tones. This variation reflects intrinsic chemical heterogeneity among the sapphires, particularly differences in Fe/Ti ratios and secondary trace-element concentrations, rather than atmospheric or thermal non-uniformity. Fuel composition note: The LPG employed conformed to the pre-2020 regional specification (≈40 vol% propane / 60 vol% butane). The higher butane fraction increases the effective carbon-to-oxygen potential of the combustion atmosphere relative to contemporary fuel blends, facilitating access to the strongly reducing conditions required for deep blue color saturation. (Themelis, 1998-2024).

5.2. Thermal Uniformity. Thermal uniformity within the furnace is as important as the absolute temperature level. Non-uniform heating can produce pronounced zoning effects, such as stones exhibiting deep blue rims with pale or colorless cores. Such outcomes commonly arise from uneven gas flow, excessive furnace loading, or misaligned burner geometry, all of which generate localized temperature gradients.

5.3. Heating and cooling rates. These parameters significantly influence the final quality of the gemstone:

- **Heating Phase:** Excessively rapid heating can induce thermal stress, micro-cracking, and the generation of structural defects that scatter light, thereby weakening the perceived color.
- **Cooling Phase:** The cooling rate governs whether color-producing defect states are preserved ("locked in") or partially lost as the furnace returns to ambient conditions during cooling.

5.4. Note. Because temperature measurement in combustion-driven furnaces is often indirect and subject to systematic error, reported soak temperatures should be regarded as relative indicators rather than absolute values. Consequently, maintaining consistency and repeatability in thermal protocols is of greater importance than reliance on a single numerical nominal temperature.

6. Kinetic Limitations and Rutile Dissolution

The development of blue coloration in geuda sapphires is governed by time-dependent diffusion processes rather than instantaneous chemical reactions. Among the most critical of these processes are the thermal dissolution of rutile (TiO_2) inclusions and the subsequent migration of titanium into the corundum lattice.

At elevated temperatures, iron diffuses relatively readily, whereas titanium exhibits markedly slower mobility. Owing to its higher ionic charge, titanium migrates through vacancy-assisted pathways within the crystal structure. As a result, titanium availability and mobility frequently constitute the rate-limiting steps in the formation of a uniform blue color.

The concentration and mobility of aluminum vacancies, which facilitate titanium diffusion, are strongly influenced by furnace oxygen partial pressure. Lower oxygen potentials promote vacancy formation, while more oxidizing conditions suppress their availability. Consequently, furnace atmosphere and soak duration act in concert to determine the depth and uniformity of titanium incorporation within the crystal.

In addition, the slow inward diffusion of oxygen can impose a further kinetic constraint. Even when appropriate redox conditions are established at the surface, the interior of the sapphire may remain chemically unaffected for extended periods. This kinetic mismatch commonly produces stones with strongly colored outer zones and weakly colored or colorless cores.

For these reasons, insufficient soak duration is a frequent cause of treatment failure. Short heating cycles may yield superficial coloration without achieving internal equilibration. Although extended soaking promotes more complete diffusion and defect stabilization, it simultaneously increases sensitivity to atmospheric instability, raising the risk of oxidation, over-reduction, or surface degradation if furnace conditions are not carefully controlled.

Fig.4. Overview of a Lakmini gas–oxygen combustion furnace employed for high-temperature thermal enhancement of geuda-type sapphires. (Themelis, 1995)

7. Trace-Element Interference: The Magnesium Ceiling

Beyond the primary roles of iron and titanium, secondary trace elements can significantly influence heat-treatment outcomes in sapphire. Among these, magnesium (Mg) is particularly important due to its direct interference with the mechanisms responsible for blue color development.

Magnesium competes with iron for interaction with titanium within the corundum lattice. When present, magnesium preferentially forms stable magnesium–titanium complexes that do not contribute to blue coloration. This interaction effectively sequesters titanium, reducing its availability for participation in iron–titanium defect states associated with blue color formation.

When magnesium concentration is high relative to titanium, the stabilization of blue color becomes increasingly unlikely, even under well-controlled thermal and atmospheric conditions. In such cases, heat treatment may produce only weak coloration or no blue response at all. This compositional limitation is referred to here as the magnesium ceiling.

Accordingly, a necessary chemical prerequisite for successful blue sapphire enhancement is that titanium be present in sufficient excess relative to magnesium. When this condition is not satisfied, treatment failure is primarily governed by intrinsic crystal chemistry rather than by furnace operation or process control. Recognition of the magnesium ceiling is therefore essential to avoid misattributing chemically constrained outcomes to equipment instability or procedural error.

PART C. MECHANICAL INCONSISTENCIES WITHIN GAS-FIRED FURNACE SYSTEMS

8. Mechanical Etiology of Failure

Even when sapphire chemistry and nominal combustion parameters are appropriately aligned, treatment success remains highly sensitive to mechanical integrity. In gas-fired sapphire furnaces, hardware-related inconsistencies frequently constitute the dominant cause of treatment failure.

Lakmini furnaces operate under sustained extremes of temperature and fuel-rich combustion. Under such conditions, critical components—burners, flowmeters, regulators, refractory linings, and gas delivery paths—undergo gradual wear, drift, and degradation. These changes often occur incrementally and may not be apparent during routine operation, yet they can substantially alter gas-flow behavior, temperature uniformity, and oxygen potential within the furnace hot zone.

Mechanical failures in these systems rarely present as abrupt or catastrophic events. Instead, they typically manifest as subtle deviations, including progressive flowmeter bias, burner misalignment, nozzle fouling, or refractory erosion. Individually minor, these effects accumulate over time and can displace the furnace atmosphere outside the narrow stability window required for blue color development. Because this drift is gradual, operators may continue to apply familiar and historically successful settings that no longer correspond to the intended internal conditions.

Accordingly, treatment failure should not be interpreted as evidence of flawed thermodynamic or chemical principles. Rather, it reflects the practical reality that furnace systems evolve with use, and that uncorrected mechanical drift can override otherwise sound process design. Recognition of mechanical etiology is therefore essential to any realistic analysis of failure in gas-combustion sapphire treatment.



Fig.5. LPG and oxygen flowmeters utilized for atmosphere control in the Lakmini combustion furnace. (Themelis, 2024).

9. LPG–O_2 Ratio Variance and Adjustment Framework

9.1. Climatic Temperature Effects. Ambient temperature influences LPG vaporization behavior and regulator performance. Under Sri Lankan operating conditions, daily temperature variations of approximately 26–34 °C modify LPG vapor pressure and downstream pressure stability. These variations alter the effective propane–butane ratio delivered to the furnace over time, producing systematic shifts in oxygen demand at otherwise unchanged flowmeter settings.

9.2. LPG Tank Composition Tolerance. Commercial LPG is supplied with a nominal propane–butane specification but permits composition tolerances on the order of ±4%. During tank draw-down, propane preferentially vaporizes due to its higher vapor pressure, progressively enriching the remaining liquid phase in butane. The combined effect of permitted supply tolerance and in-tank fractionation modifies the carbon-to-hydrogen ratio of the delivered fuel, thereby displacing both the Titration Point (TP) and the Soot Disappearance Boundary (SDB) along the nominal LPG:O_2 axis if uncorrected.

9.3. Flow Indication and Manual Adjustment Bias. Gas delivery in Lakmini furnaces is controlled using air-calibrated analog flowmeters (rotameters) and manually adjusted regulator valves without pressure gauges. When used with oxygen and LPG, these instruments exhibit systematic bias due to gas-density mismatch, mechanical wear, and non-linear float response. In particular, the higher density of oxygen relative to air causes true oxygen flow to be lower than indicated, biasing the furnace atmosphere toward oxidation. Furthermore, at high LPG flow rates, the rapid vaporization of fuel can induce significant cooling of the Lakmini's pressure regulators, leading to pressure fluctuations or "pulsing." These short-term instabilities trigger oscillations in the oxygen partial pressure within the hot zone, even

when flowmeter settings appear superficially stable. Manual adjustment further introduces operator-dependent variability, even when indicated readings appear stable.

9.4. Sri Lankan Lakmini Adjustment Factor and Operational Consequence. When climatic variability, LPG composition tolerance (±4%), and air-calibrated flowmeter bias are considered together, the LPG–O_2 ratios indicated on Lakmini flowmeters do not represent the effective gas balance within the furnace. To first order, these effects may be consolidated into a single Sri Lankan adjustment factor relating indicated to effective LPG–O_2 ratios. Under typical operating conditions, this factor is bounded rather than constant, lying approximately within the range 0.83–0.90, depending on time of day, tank state, and regulator behavior. Application of this adjustment shifts the operational trajectory laterally in oxygen-potential space, displacing both TP and SDB relative to their apparent positions on the indicated LPG–O_2 axis.

Fig. 6. Degradation of the furnace heating chamber following repeated thermal cycling. Prolonged exposure to high temperatures has induced cracking and surface spalling of the hot-face refractory lining. The presence of loosened insulation material in the secondary layer indicates progressive refractory degradation under service conditions. The handmade crucible exhibits advanced structural damage, which can perturb local temperature uniformity and furnace atmosphere, directly affecting the sapphires processed within. Themelis, 2004).

9.5. Illustrative Example. An operator observing 6 units LPG and 27 units O_2 on air-calibrated flowmeters installed in the Lakmini would infer an indicated LPG:O_2 ratio of approximately 1:4.5, commonly interpreted as lying within the optimal blue-color regime. Applying a representative adjustment factor of ~0.85 shifts the effective ratio toward ~1:3.8, moving the furnace atmosphere closer to, or below, the soot-stability boundary in oxygen-potential space. In such cases, color degradation or surface carbon deposition may occur despite unchanged flowmeter settings. This example is diagnostic, not prescriptive, and illustrates the direction and magnitude of trajectory displacement and does not constitute a recommended operating condition.

10. Refractory Chemical Surface Corrosion and Degradation

At the temperatures required for sapphire heat treatment, the refractory materials forming the Lakmini furnace hot face become chemically active. When these linings lack sufficient purity or are inadequately sintered, trace constituents may be released into the furnace atmosphere during prolonged operation.

Refractories containing iron- or silicon-bearing phases are particularly susceptible under sustained temperatures near or above 1650 °C. Under fuel-rich conditions, these components may volatilize or participate in gas–solid reactions, generating reactive species capable of interacting with sapphire surfaces. Such interactions can lead to the formation of iron–silicate or related reaction layers at the stone–atmosphere interface.

The resulting degradation is best described as chemical surface corrosion. The formation of low-melting reaction products promotes localized surface melting, pitting, and roughening, increasing light scattering and imparting a frosted or etched appearance to the sapphire. Once established, this form of surface damage is not reversible by further heat treatment and often not recoverable.

Failures arising from refractory instability therefore represent a distinct class of treatment loss, independent of furnace atmosphere control or intrinsic sapphire chemistry.

12. Thermometry and Radiation Lag



Fig.7. Type-B thermocouple assembly used in a Lakmini furnace. The visible pink discoloration of the thermoelement wires is consistent with rhodium-related chemical degradation following prolonged exposure to high-temperature, fuel-rich conditions. The use of non-matching extension leads and a simple jack-type connector introduces additional sources of measurement error through junction mismatch and parasitic thermoelectric voltages. These combined effects can result in systematic temperature offsets, limiting the reliability of thermometric control during sapphire heat treatment.

Accurate temperature measurement in gas-fired sapphire furnaces is inherently challenging. Many Lakmini systems rely on Type B thermocouples that sample the local flame environment rather than the true thermal state of the crucible or gemstone. The resulting signal represents a composite of flame radiation, furnace wall emission, and conductive heat loss along the ceramic sheath. Depending on sensor placement and furnace geometry, the indicated temperature may differ substantially from the effective hot-zone temperature experienced by the sapphires.

In the fuel-rich, reducing atmospheres required for blue sapphire treatment, rhodium-based thermoelements are additionally susceptible to chemical degradation. Reduction of oxide layers, contamination by metallic vapors, and gradual embrittlement of the wires can induce thermoelectric drift without obvious external damage. As a result, thermocouple readings are best interpreted as relative indicators of operating conditions rather than as absolute measures of gemstone temperature.

Optical techniques, such as two-color ratio pyrometry, offer an alternative approach with reduced sensitivity to emissivity variation and chemical attack. However, these instruments are line-of-sight dependent and require careful alignment and a stable optical path through the furnace atmosphere, conditions that are not always achievable in production-scale Lakmini furnaces.

13. Atmospheric Stratification

In a properly engineered furnace, fuel and oxygen would mix uniformly, producing a consistent atmosphere throughout the hot zone. In Lakmini gas-fired furnaces, however, this condition is seldom achieved. Variations in burner alignment, gas velocity, and chamber geometry frequently lead to spatial segregation of the combustion atmosphere, resulting in regions with differing oxygen partial pressures—a phenomenon referred to as atmospheric stratification.

Under stratified conditions, localized zones within the furnace may become oxidizing while adjacent regions remain strongly reducing, even when flowmeter settings are held constant. Sapphires positioned at different locations within the same load may therefore experience markedly different redox environments. This spatial heterogeneity provides a practical explanation for mixed treatment outcomes, where some stones exhibit color loss while others, only centimeters away, undergo over-reduction or develop metallic masking.

Insufficient gas mixing also reduces effective gas residence time, limiting the duration over which reactive species interact with the sapphires. Shortened residence times diminish atmospheric stability and increase sensitivity to minor flow or pressure fluctuations at the burner. These effects are particularly pronounced under fuel-rich operating conditions, where the combustion process already operates near critical redox boundaries.

Atmospheric stratification thus represents a significant source of process variability in Lakmini furnaces. It further explains why changes in sapphire placement or burner alignment can substantially influence treatment outcomes, even when nominal LPG–O_2 ratios remain unchanged.

14. Burner Nozzle Fouling and Alignment

Under fuel-rich operating conditions, Lakmini burner nozzles gradually accumulate soot and carbonaceous deposits. This buildup develops progressively over the course of a heating cycle and can reach functionally significant levels within several hours. Even modest deposition is sufficient to disrupt the initial mixing of LPG and oxygen prior to entry into the furnace chamber.

Partial nozzle fouling alters gas-flow symmetry, producing distorted flame profiles with localized regions of elevated or suppressed temperature. These distortions translate into spatial variations in oxygen potential within the hot zone, exposing sapphires at different positions to dissimilar redox environments despite constant indicated gas settings.

Burner alignment is equally critical. Minor deviations in nozzle orientation or centering can cause flame impingement on the refractory lining, leading to asymmetric heating and non-uniform atmospheric conditions. Under fuel-rich combustion, such misalignments may locally shift the atmosphere toward oxidation or excessive reduction, narrowing or eliminating the effective blue-color window.

Routine cleaning and precise alignment of burner nozzles are therefore essential for maintaining atmospheric stability. In many instances, restoring proper burner geometry has a greater impact on treatment outcomes than further adjustment of nominal LPG–O_2 ratios.

15. Methodological Limitations and Visual Proxies

In routine Lakmini furnace operation, flame appearance is commonly used as a qualitative indicator of internal atmospheric conditions. While visual inspection can provide useful preliminary information, reliance on flame morphology alone introduces inherent methodological limitations when assessing the oxygen potential relevant to blue sapphire formation.

Distinct LPG–O_2 ratios may produce flames that appear visually similar, even though the resulting oxygen partial pressures within the furnace hot zone differ substantially. Slightly oxidizing and mildly reducing atmospheres, for example, can exhibit comparable flame color, brightness, and geometry when viewed through observation ports. As a result, visual similarity does not reliably indicate that conditions fall within the narrow redox window required for stable blue coloration.

A related source of variability arises from furnace loading practices. When the Lakmini chamber is heavily loaded, gas circulation around individual stones may become uneven. Some specimens experience continuous exposure to reactive gases, while others reside in regions of reduced flow or partial stagnation. This non-uniformity leads to spatial variations in temperature and oxygen potential within a single run, producing mixed outcomes even under otherwise consistent operating settings.

For these reasons, visual flame inspection is best regarded as a supplementary diagnostic rather than a primary control parameter. Consistent treatment outcomes require the coordinated control of gas-flow ratios, burner condition, furnace geometry, and loading configuration. Flame appearance alone is insufficient to characterize the complex atmospheric conditions governing high-temperature sapphire heat treatment.

16. Summary of Failure Etiology

16.1. Overview. The successful heat treatment of blue sapphire requires the concurrent stabilization of multiple interdependent variables. Treatment failure does not arise from deficiencies in the underlying thermodynamic or crystal-chemical models, but rather from the difficulty of maintaining all critical parameters within their respective operational bounds simultaneously. When one or more variables drift beyond these limits, blue coloration may weaken, fail to develop, or transition into undesired gray or greenish tones. Based on the present analysis, treatment outcomes in Lakmini furnaces may be understood in terms of three principal etiological categories:

16.2. Intrinsic crystal chemistry. Certain geuda sapphires lack the chemical prerequisites for stable blue coloration. In particular, insufficient titanium content or magnesium concentrations exceeding the

effective “magnesium ceiling” prevent the formation or stabilization of iron–titanium-related defect states. In such cases, treatment outcome is governed primarily by intrinsic crystal chemistry rather than by furnace operation.

16.3. Atmospheric and thermal thresholds. Stable blue coloration is restricted to a narrow oxygen-potential interval at elevated temperatures. Excess oxygen promotes oxidation and destabilization of color-producing defect states, leading to color loss or “color crash.” Conversely, insufficient oxygen favors over-reduction, resulting in metallic gray masking or carbon-related surface effects. The effective operational window therefore exists only within a tightly bounded combination of temperature and LPG–O_2 ratio.

16.4. Mechanical and operational variability. Hardware-related factors represent a major source of process variability. Progressive drift in flowmeter accuracy, burner fouling or misalignment, LPG composition fluctuations, refractory degradation, and thermometry uncertainty can each shift the furnace atmosphere away from the optimal operating regime. Because these changes often develop incrementally, departures from the blue stability window may occur without obvious changes in nominal operating settings.

These etiological categories emphasize that treatment failure is rarely attributable to a single isolated cause. Instead, failure reflects the cumulative effect of chemical limitations, thermodynamic thresholds, and mechanical variability acting within a tightly constrained process window.

Conclusion

This study demonstrates that successful blue sapphire heat treatment depends on the precise synchronization of gemstone chemistry, furnace atmosphere, and mechanical system performance. Stable coloration develops only when these elements remain balanced within a narrow operational corridor. Central to this process is the management of oxygen potential: excessive oxygen destabilizes Fe^{2+}–Ti^{4+} defect states, while conditions exceeding the reducing limit promote reactions—such as metallic precipitation—that obscure the desired hue.

In gas-fired Lakmini furnaces, the oxygen potential is an emergent property of LPG–oxygen stoichiometry and combustion dynamics. Consequently, treatment failures typically stem not from an incorrect conceptual target, but from unrecognized shifts in burner condition, gas composition, or mechanical calibration. These deviations displace the internal atmosphere beyond the Titration Point (TP) or the Soot Disappearance Boundary (SDB), leading to oxidation-driven color loss or soot-induced masking.

By categorizing these failure mechanisms, this work advances sapphire treatment from empirical trial-and-error toward a thermodynamically grounded engineering framework. While Lakmini furnaces possess inherent variability, the blue sapphire “window” must be understood as a bounded operating range requiring active stabilization rather than static point control. Recognizing and managing these subtle mechanical shifts is essential for improving the consistency and economic reliability of blue sapphire processing.

Economic Implications of Thermodynamic Instability

The thermodynamic variability identified in this study carries profound implications for the socioeconomic equilibrium of the Sri Lankan gemstone sector. An export industry valued at approximately $360 million (official) currently relies on a primary fleet of fewer than 500 Lakmini-class furnaces, managed by a specialized cadre of roughly 1,000 practitioners. A critical professional gap remains: while academic gemologists often possess 'certificate or diploma-level' credentials, they frequently lack the engineering and thermodynamic depth required to diagnose system-level failures. Conversely, the artisanal operators remain tethered to 'secret recipes' and empirical intuition.

Because physics possesses no secrets—only fundamental constants awaiting discovery—the reliance on ritual over measurement remains a point of national vulnerability. This study suggests that introducing proper atmospheric stabilization—achievable at comparable modest cost—would empower practitioners to transcend legacy limitations. By aligning artisanal experience with thermodynamic precision, the

industry can secure high-value corundum assets, often exceeding tens of thousands of dollars per unit, against the mechanical drift that currently dictates the success or failure of the nation's primary value-added export.

REFERENCES:

Amphon, R., Chankhantha, C., Srimuang, C., Vongsetskul, S., Intarasiri, S., & Shen, A. H. (2024). Changes in blue color of sapphire compared with oxidation state changes. Minerals, 14(4), 333

Burns, R. G., & Strens, R. G. J. (1966). Infrared absorption of transition metal ions in silicate minerals. Science, 153(3736), 890–892.

Burns, R. G. (1970). Mineralogical Applications of Crystal Field Theory. Cambridge: Cambridge University Press.

Ediriweera, R.N., Perera S.I., (1987). Heat treatment of Geuda stones – spectral investigation. Journal of Gemmology, Vol.21, 7.

Eigenmann, K., & Günthard, Hs. H. (1972). The optical absorption of Fe^{2+}–Ti^{4+} pairs in sapphire.

Nassau, K. (1981). The Physics and Chemistry of Color: The Fifteen Causes of Color. New York: John Wiley & Sons.

Thammajaka, N., & Klondona, R. (2023). Fe K-edge and Ti K-edge XAS study of blue sapphires (Conference Abstract). Advanced Materials Testing and Characterization, MTEC 2023.

Wongrawang, P., Monarumit, N., Thammajak, N., Wathanakul, P., & Wongkokua, W. (2016). Oxidation states of Fe and Ti in blue sapphire. Materials Research Express, 3(2), 026201. DOI:10.1088/2053-1591/3/2/026201

Themelis, T. (1987-2025). Heat Treatment of Ruby & Sapphire: A Systematic Analysis of Thermodynamic and Mechanical Failure (Vols. 1-12) [Unpublished monograph manuscript series]. Private Archive of the Author.

About the author. Ted Themelis is an independent researcher in ruby and sapphire heat treatment, based in Bangkok, Thailand, with work ongoing since 1984. Research activities are self-funded and strictly laboratory-based. Involved in the design, fabrication, and sale of innovative gem treatment equipment. Author of more than 100 publications. Widely recognized as an authority in corundum treatments.